

# Yb-MCOF-35/250-05-2.0-PM

## PM Yb-Doped Large Mode Area Fiber

The Yb-MCOF-35/250-PM fibers are designed for  $M^2$  lower than 1.15 making it the perfect choice for applications requiring superior beam quality. Our fiber design features a confined core for selective gain amplification and multi-layer cladding for superior suppression of higher order modes.



### SPECIFICATIONS

Optical Properties	
Core NA	0.05 ± 0.01
Cladding NA	> 0.47
Pump guide absorption @ 915 nm	2.0 ± 0.4 dB/m
Nominal pump guide absorption @ 975 nm	8.0 dB/m
Birefringence	≥ 1.4 × 10 <sup>-4</sup>
Beam quality factor $M^2$	< 1.15
Physical Properties	
Optical cladding	Multi
Core diameter	35.0 ± 3.0 μm
Silica cladding diameter	250.0 ± 5.0 μm
Coating diameter	390.0 ± 20.0 μm
Cladding geometry	Round
Screen proof tested	≥ 100 kpsi
Recommended coiling diameter	≥ 25 cm
Confined core	Yes
Depressed cladding	Yes

### Features

- Designed for output  $M^2$  lower than 1.15
- Large core diameter of 35 μm
- Low photodarkening
- High birefringence
- Confined core for selective gain amplification
- Increased differential bending losses
- Designed to amplify narrow linewidth seed lasers operated in pulsed mode

### Typical Applications

- Material processing
- Frequency conversion
- Biophotonics
- Range finding

# Yb-MCOF-35/250-05-2.0-PM

## PM Yb-Doped Large Mode Area Fiber

3 versions of this fiber are available. Please refer to the table below for specifications comparison.

### SPECIFICATIONS COMPARISON TABLE

Optical Properties	Yb-MCOF-35/250-07-0.9-PM	Yb-MCOF-35/250-07-2.5-PM	Yb-MCOF-35/250-05-2.0-PM
Core NA	0.07 ± 0.01		0.05 ± 0.01
Cladding NA	> 0.47		
Pump guide absorption @ 915 nm	0.9 ± 0.1 dB/m	2.5 ± 0.5 dB/m	2.0 ± 0.4 dB/m
Nominal pump guide absorption @ 975 nm	4.0 dB/m	10.0 dB/m	8.0 dB/m
Birefringence	$\geq 1.4 \times 10^{-4}$		
Beam quality factor M <sup>2</sup>	< 1.15		
Physical Properties	Yb-MCOF-35/250-07-0.9-PM	Yb-MCOF-35/250-07-2.5-PM	Yb-MCOF-35/250-05-2.0-PM
Optical cladding	Multi		
Core diameter	35.0 ± 3.0 µm		
Silica cladding diameter	250.0 ± 5.0 µm		
Coating diameter	390.0 ± 20.0 µm		
Cladding geometry	Round		
Screen proof tested	≥ 100 kpsi		
Recommended coiling diameter	≥ 12 cm	≥ 14 cm	≥ 25 cm
Confined core	Yes		
Depressed cladding	Yes		

**R&D CONTRACTS – PROTOTYPING – PREPRODUCTION**  
**SHORT-RUN PRODUCTION – TECHNOLOGY TRANSFERS**